

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

12

EUROPEAN PATENT APPLICATION

21 Application number: 80850052.4

51 Int. Cl.³: C 03 C 13/00

22 Date of filing: 15.04.80

30 Priority: 09.05.79 SE 7904044

43 Date of publication of application:
26.11.80 Bulletin 80/24

58 Date of deferred publication of search report: 20.05.81

84 Designated Contracting States:
BE DE FR GB IT NL

71 Applicant: OY PARTEK AB

SF-21600 Pargas(FI)

72 Inventor: Carbol, Vlastimil
Alpgatan 20
S-352 41 Växjö(SE)

74 Representative: Wiklund, Erik et al,
AWAPATENT AB Box 5117
S-200 71 Malmö(SE)

54 Fiber glass composition.

57 A fibre glass composition which is characterised in that it
consists of

	% by weight
SiO ₂	55 - 65
Al ₂ O ₃	1 - 2
CaO	6 - 9.5
MgO	1 - 4.5
Na ₂ O	13 - 17
K ₂ O	0 - 2
B ₂ O ₃	1 - 7
BaO	0 - 3
Li ₂ O	0 - 1
Fe ₂ O ₃	traces
ZnO	0.5 - 6

EP 0 019 600 A3

0019600



European Patent
Office

EUROPEAN SEARCH REPORT

Application number
EP 80 35 0052

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int. Cl. 8)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
	<p><u>GB - A - 811 243</u> (OWENS-CORNING FIBERGLAS)</p> <p>* Page 1, lines 11-14; claim 1 *</p> <p>--</p> <p><u>FR - A - 2 202 048</u> (JOHNS-MANVILLE)</p> <p>* Page 4, lines 2-13 *</p> <p>--</p> <p>A CHEMICAL ABSTRACTS, vol. 89, no. 4, 24th July 1978, page 322, column 2, no. 29556j. Columbus, Ohio, U.S.A.</p> <p>& JP - A - 78 02515 (ASAHI GLASS, 11-01-1978)</p> <p>--</p> <p>A <u>FR - A - 2 210 581</u> (OWENS-CORNING FIBERGLAS)</p> <p>A <u>DE - A - 2 847 283</u> (JOHNS-MANVILLE)</p> <p>----</p>	<p>1,2</p> <p>1</p>	<p>C 03 C 13/00</p>
			TECHNICAL FIELDS SEARCHED (Int. Cl. 8)
			C 03 C 13/00
			CATEGORY OF CITED DOCUMENTS
			<p>X: particularly relevant</p> <p>A: technological background</p> <p>O: non-written disclosure</p> <p>P: intermediate document</p> <p>T: theory or principle underlying the invention</p> <p>E: conflicting application</p> <p>D: document cited in the application</p> <p>L: citation for other reasons</p>
			&: member of the same patent family, corresponding document
<p>The present search report has been drawn up for all claims</p>			
Place of search		Date of completion of the search	Examiner
The Hague		19-02-1981	GAJ

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

SCIENCE REFERENCE LIBRARY

(11)

Publication number:

**0 019 600
A2**

(12)

EUROPEAN PATENT APPLICATION

(21)

Application number: 80850052.4

(51)

Int. Cl.³: C 03 C 13/00

(22)

Date of filing: 15.04.80

(30)

Priority: 09.05.79 SE 7904044

(43)

Date of publication of application:
26.11.80 Bulletin 80/24

(84)

Designated Contracting States:
BE DE FR GB IT NL

(71)

Applicant: OY PARTEK AB

SF-21600 Pargas(FI)

(72)

Inventor: Carbol, Vlastimil
Alpgatan 20
S-352 41 Växjö(SE)

(74)

Representative: Wiklund, Erik et al.
AWAPATENT AB Box 5117
S-200 71 Malmö(SE)

(54)

Fiber glass composition.

(57)

A fibre glass composition which is characterised in that it consists of

% by weight

SiO ₂	55 - 65
Al ₂ O ₃	1 - 2
CaO	6 - 9.5
MgO	1 - 4.5
Na ₂ O	13 - 17
K ₂ O	0 - 2
B ₂ O ₃	1 - 7
BaO	0 - 3
Li ₂ O	0 - 1
Fe ₂ O ₃	traces
ZnO	0.5 - 6

EP 0 019 600 A2

FIBRE GLASS COMPOSITION

This invention relates to a glass composition for the production of fibres for glass wool insulations. The glass composition according to the invention is especially suited for the so-called Johns-Manville fibre forming process which utilizes a process equipment incapable of withstanding excessive temperatures.

In the conventional production of such fibres, molten glass is extruded by centrifugal force through the apertures of a rotary spinner. In order to obtain satisfactory fibres, the glass should fulfil certain requirements. Thus, the melting temperature and the fibre forming temperature of the glass must be low, thereby to impart maximum life to the spinner. The melting temperature is indicated as the so-called log 2 temperature, i.e. the temperature at which the 10^{\log} of the viscosity of the glass, measured in poise (or deciPascalsecond, dPas) is 2, while the fibre forming temperature is correspondingly given as the log 3 temperature. If the log 2 and log 3 temperatures can be lowered, this will increase the life of the spinner, and the production stops necessitated by the exchange of the spinners will be less frequent. Already a lowering of the log 2 and log 3 temperatures by five or ten $^{\circ}\text{C}$ constitutes a considerable improvement. However, a lowering of only the log 2 temperature and the log 3 temperature of the glass is not feasible since the other properties of the glass must also be taken into consideration.

Among the remaining important properties of the glass that must be taken into consideration, is the liquidus temperature, L_T , which is the temperature above which no crystallization occurs in the glass. To avoid crystallization of the glass in the spinner, the liquidus temperature must lie at least 50°C below the log 3 temperature.

Another important property of the glass is its chemical resistance which is measured in accordance with standardized testing methods as the so-called hydrolytical resistance (P value or DGG value).

5 If it is desired to lower the melting temperature and the fibre forming temperature of the glass, the obvious thing is to increase the content of CaO , Na_2O , K_2O or B_2O_3 . However, an increase of the CaO content will result in an increase of the liquidus temperature
10 of the glass, with the ensuing risk of crystallization in the spinner. An increased content of Na_2O , K_2O or B_2O_3 reduces the chemical resistance of the glass. It will thus be obvious that there is little possibility of changing the composition in conventional manner to
15 obtain improved properties in one respect, without simultaneously deteriorating the properties in some other respect.

The present invention, however, the characteristic features of which are stated in the appended claims,
20 quite surprisingly yields a glass composition having essentially improved properties as compared with standard glass, and this is achieved by incorporating ZnO and preferably also Li_2O in the glass composition.

The invention is based on the fact that there exists
25 between certain atomic types in the glass, such as Zn-Ca and Li-Na-K, a certain anomaly which is of decisive importance to the physical properties of the glass and which depends upon the ion radii of the atoms. To satisfy this anomaly, the difference between the ion radii
30 must be greater than 0.3 Å. In order to improve the physical and chemical properties of the glass, this anomaly in the glass structure must be well satisfied, and this means that certain atoms should be included in the glass in a specific interrelationship.

35 In the light of these circumstances, the present invention proposes incorporating ZnO in the glass, thereby to change the physical and, in particular, the chemical

properties of the glass. Furthermore, it is especially preferred to incorporate also from 0 to 1, preferably from 0.1 to 0.4% by weight of Li_2O in the glass, whereby the anomaly is further improved, the viscosity is greatly reduced, and the chemical resistance of the glass is increased.

The fibre glass according to the present invention is characterised by a composition which, based on % by weight, lies within the following general limits:

		<u>% by weight</u>
0	SiO_2	55 - 65
	Al_2O_3	1 - 2
	CaO	6 - 9.5
	MgO	1 - 4.5
5	Na_2O	13 - 17
	K_2O	0 - 2
	B_2O_3	1 - 7
	BaO	0 - 3
	Li_2O	0 - 1
10	Fe_2O_3	traces
	ZnO	0.5 - 6

It is especially preferred that the glass composition according to the present invention lie within the following limits:

		<u>% by weight</u>
	SiO_2	58 - 62
	Al_2O_3	1 - 2
	CaO	8 - 9.5
30	MgO	2.3 - 3.5
	Na_2O	15 - 17
	K_2O	0 - 1
	B_2O_3	5 - 7
	BaO	-
35	Li_2O	0.1 - 0.4
	Fe_2O_3	traces
	ZnO	1.5 - 3.5

By adding from 0.5 to 6, preferably from 1.5 to 3.5% by weight of ZnO, an excellent chemical resistance of the glass according to the invention is obtained. The chemical resistance was even found to be much better than when the same amount of, for example, titanium dioxide is added to the glass.

Generally, a high proportion of alkali in alkali borosilicate glass greatly reduces the chemical resistance of the glass, but if ZnO is supplied to such glass, the surprising result is that the glass may contain larger amounts of alkali without detriment to the chemical resistance.

The high alkali content, on its part, affects the viscosity of the glass according to the invention so that it will be more readily liquefiable, i.e. the log 2 and log 3 temperatures of the glass are lowered, and this brings a number of practical advantages, such as a lower fibre forming temperature, whereby the life of the fibre forming equipment will be extended and power can be saved. The lower fibre forming temperature also gives a product of higher quality. Furthermore, the glass according to the invention shows a lowering of the liquidus temperature as compared with conventional glass, as a result of which the risk of crystallization of the glass in the spinner is conspicuously reduced or even eliminated. In addition, the glass according to invention has excellent chemical resistance, as will appear from the values of hydrolytical resistance in the following Examples. A further advantage of the present invention is that readily available and inexpensive ZnO-containing starting material may be used. Thus, there is no need to use absolutely pure ZnO as the starting material for the ZnO content of the glass, and any ZnO-containing material can be used.

To illustrate the present invention, the following non-restrictive Examples are given.

EXAMPLES 1-4

Three ZnO-containing glasses according to the present invention were produced. For the purpose of comparison, a conventional alkali borosilicate glass was produced which is used in actual practice and which in the following is referred to as "standard glass".

The compositions of the standard glass and the glass according to the present invention, like the properties of the glasses with respect to $\log \eta$, $\log \eta$, L_T , liquidus viscosity and chemical resistance ($P_{V,SIS}$ 136 321) will appear from Table 1.

TABLE 1

Oxide	Example 1 (standard glass)	Example 2	Example 3	Example 4
SiO_2	63.0	62.6	59.2	56.4
Al_2O_3	2.5	1.5	1.5	1.5
CaO	8.8	9.1	9.1	9.1
MgO	3.5	3.5	3.5	3.5
Na_2O	14.7	15.9	15.9	15.9
K_2O	1.0	0.6	0.6	0.6
B_2O_3	6.5	6.9	6.9	6.9
BaO	-	-	-	-
Li_2O	-	0.2	0.2	-
Fe_2O_3	0.2	0.1	0.1	0.1
ZnO	-	0.5	3.0	6.0
$\log \eta$ 2 ($^{\circ}C$)	1270	1200	1187	1162
$\log \eta$ 3 ($^{\circ}C$)	1060	997	992	973
L_T ($^{\circ}C$)	960	948	920	1064
Liquidus				
visc.	3.699	3.353	3.528	2.440
$P_{V,SIS}$				
136232	1.0	1.5	0.9	0.75

CLAIMS

1. Fibre glass composition, characterised in that it consists of

		<u>% by weight</u>
5	SiO ₂	55 - 65
	Al ₂ O ₃	1 - 2
	CaO	6 - 9.5
	MgO	1 - 4.5
	Na ₂ O	13 - 17
10	K ₂ O	0 - 2
	B ₂ O ₃	1 - 7
	BaO	0 - 3
	Li ₂ O	0 - 1
	Fe ₂ O ₃	traces
15	ZnO	0.5 - 6

2. A fibre glass composition as claimed in claim 1, characterised in that it consists of

		<u>% by weight</u>
20	SiO ₂	58 - 62
	Al ₂ O ₃	1 - 2
	CaO	8 - 9.5
	MgO	2.5 - 3.5
	Na ₂ O	15 - 17
25	K ₂ O	0 - 1
	B ₂ O ₃	5 - 7
	BaO	-
	Li ₂ O	0.1 - 0.4
	Fe ₂ O ₃	traces
	ZnO	1.5 - 3.5